

***NATIONAL ANNEX
TO
CYS EN 1996-3:2006
(Including AC:2009)***

***Eurocode 6: Design of
masonry structure***

***Part 3: Simplified
calculation methods
for unreinforced
masonry structures***



NATIONAL ANNEX
TO
CYS EN 1996-3:2006 including AC:2009
Eurocode 6: Design of masonry structures
Part 3: Simplified calculation methods for unreinforced
masonry structures

This National Annex has been approved by the Board of Directors of the Cyprus Organisation for Standardisation (CYS) on 14.06.2019.

Copyright

Right to reproduce and distribute belongs to the Cyprus Organisation for Standardisation.

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Cyprus Organisation for Standardisation.

If you have any questions about standards copyright, please contact Centre of Information and Customer Service at the Cyprus Organisation for Standardisation phone: +357 22 411413/4 email: c.service@cys.org.cy

INTRODUCTION

This National Annex has been prepared by the CYS TC 18 National Standardisation Technical Committee of Cyprus Organisation for Standardisation. (CYS)

NA 1 SCOPE

This National Annex is to be used together with CYS EN 1996-3:2006 including AC:2009.

Any reference in the rest of this text to CYS EN 1996-3:2006 means the above document.

This National Annex gives:

(a) Nationally determined parameters for the following clauses of CYS EN 1996-3:2006+AC:2009 where National choice is allowed (see Section NA 2)

- 2.3(2)P
- 4.1(P)
- 4.2.1.1(1)P
- 4.2.2.3(1)
- D.1(1)
- D.2(1)
- D.3(1)

(b) Decisions on the use of the Informative Annexes A and C (see Section NA 3)

NA 2 NATIONALLY DETERMINED PARAMETERS

NA 2.1 Clause 2.3 Verification by the partial factor method

(2)P The relevant values of the partial factor for materials γ_M , given in clause 2.4.3 of CYS EN 1996-1-1:2005+A1:2012, shall be used for the ultimate limit state for ordinary situations.

NA 2.2 Clause 4.1 General

(1)P The overall stability of a building, of which the wall forms a part, shall be verified in accordance with 5.4(1) of CYS EN1996-1-1:2005+A1:2012

NA 2.3 Clause 4.2.1.1 General conditions for application

(1)P The numerical value to be ascribed to the symbol h_m shall be taken from the table bellow.

Class	1	2	3
h_m	20 m	16 m	12 m

NA 2.4 Clause 4.2.2.3 Capacity reduction factor

(1)P The minimum number of wall ties per m^2 , $n_{min} = 2$

NA 2.5 Clause D.1 (1) Characteristic compressive strength

The characteristic compressive strength of masonry may be calculated using the clause 3.6.1.2 of CYS EN 1996-1-1:2005+A1:2012, or from the tables bellow

Clay Units Group 1

f_b [N/mm ²]	General purpose mortar				Thin joint	Light weight mortar		
	M2,5	M5	M10	M20		M2,5	M5	M10
2	1,2	1,4	1,4	1,4	1,2	0,6	0,7	0,7
4	1,9	2,4	2,7	2,7	2,0	1,0	1,3	1,5
6	2,5	3,1	3,8	4,1	2,6	1,4	1,7	2,1
8	3,1	3,8	4,7	5,4	3,2	1,7	2,1	2,6
10	3,6	4,5	5,5	6,8	3,8	2,0	2,4	3,0
12	4,1	5,1	6,2	7,7	4,3	2,2	2,8	3,4
16	5,0	6,2	7,6	9,4	5,2	2,8	3,4	4,2
20	5,9	7,3	8,9	11,0	6,1	3,2	4,0	4,9
25	6,9	8,5	10,4	12,9	7,1	3,8	4,6	5,7
30	7,8	9,6	11,9	14,6	8,1	4,3	5,3	6,5
50	11,2	13,8	17,0	20,9	11,6	6,1	7,5	9,3
75	14,9	18,3	22,5	27,7	11,6	8,1	10,0	12,3

Clay Units Group 2

f_b [N/mm ²]	General purpose mortar				Thin joint	Light weight mortar		
	M2,5	M5	M10	M20		M2,5	M5	M10
2	1,0	1,1	1,1	1,1	1,1	0,5	0,6	0,6
4	1,6	1,9	2,2	2,2	1,8	0,9	1,1	1,2
6	2,1	2,6	3,1	3,3	2,5	1,2	1,4	1,7
8	2,5	3,1	3,8	4,4	3,0	1,4	1,7	2,1
10	3,0	3,7	4,5	5,5	3,5	1,6	2,0	2,5
12	3,4	4,2	5,1	6,3	4,0	1,9	2,3	2,8
16	4,1	5,1	6,3	7,7	4,9	2,3	2,8	3,5
20	4,8	5,9	7,3	9,0	5,7	2,7	3,3	4,1
25	5,6	6,9	8,5	10,5	6,7	3,1	3,9	4,7
30	6,4	7,9	9,7	12,0	7,6	3,6	4,4	5,4
50	9,2	11,3	13,9	17,1	10,8	5,1	6,3	7,7
75	12,2	15,0	18,4	22,7	10,8	6,8	8,3	10,2

Clay Units Group 3 and 4

f_b [N/mm ²]	General purpose mortar				Thin joint		Light weight mortar		
	M2,5	M5	M10	M20	Group 3	Group 4	M2,5	M5	M10
2	0,7	0,9	0,9	0,9	0,8	0,6	0,4	0,5	0,5
4	1,2	1,5	1,7	1,7	1,3	1,1	0,7	0,9	1,0
6	1,6	2,0	2,4	2,6	1,8	1,6	0,9	1,1	1,4
8	2,0	2,4	3,0	3,4	2,1	2,0	1,1	1,4	1,7
10	2,3	2,8	3,5	4,3	2,5	2,5	1,3	1,6	2,0
12	2,6	3,2	4,0	4,9	2,8	2,9	1,5	1,8	2,3
16	3,2	4,0	4,9	6,0	3,5	3,7	1,8	2,3	2,8
20	3,8	4,6	5,7	7,0	4,1	4,5	2,1	2,6	3,2
25	4,4	5,4	6,6	8,2	4,8	5,4	2,5	3,1	3,8
30	5,0	6,1	7,6	9,3	5,4	6,3	2,8	3,5	4,3
50	7,1	8,8	10,8	13,3	7,7	9,7	4,1	5,0	6,2
75	9,5	11,6	14,3	17,7	7,7	9,7	5,4	6,7	8,2

Calcium silicate, aggregate concrete and autoclaved aerated concrete units Group 1

f_b [N/mm ²]	General purpose mortar				Thin joint	Light weight mortar (not for calcium silicate units)		
	M2,5	M5	M10	M20		M2,5	M5	M10
2	1,2	1,4	1,4	1,4	1,4	1,0	1,1	1,1
4	1,9	2,4	2,7	2,7	2,6	1,6	1,9	2,2
6	2,5	3,1	3,8	4,1	3,7	2,1	2,6	3,1
8	3,1	3,8	4,7	5,4	4,7	2,5	3,1	3,8
10	3,6	4,5	5,5	6,8	5,7	3,0	3,7	4,5
12	4,1	5,1	6,2	7,7	6,6	3,4	4,2	5,1
16	5,0	6,2	7,6	9,4	8,4	4,1	5,1	6,3
20	5,9	7,3	8,9	11,0	10,2	4,8	5,9	7,3
25	6,9	8,5	10,4	12,9	12,3	5,6	6,9	8,5
30	7,8	9,6	11,9	14,6	14,4	6,4	7,9	9,7
50	11,2	13,8	17,0	20,9	22,2	9,2	11,3	13,9

Calcium silicate and aggregate concrete units Group 2

f_b [N/mm ²]	General purpose mortar				Thin joint	Light weight mortar (not for calcium silicate units)		
	M2,5	M5	M10	M20		M2,5	M5	M10
2	1,0	1,1	1,1	1,1	1,1	1,0	1,1	1,1
4	1,6	1,9	2,2	2,2	1,7	1,6	1,9	2,2
6	2,1	2,6	3,1	3,3	2,3	2,1	2,6	3,1
8	2,5	3,1	3,8	4,4	2,8	2,5	3,1	3,8
10	3,0	3,7	4,5	5,5	3,3	3,0	3,7	4,5
12	3,4	4,2	5,1	6,3	3,7	3,4	4,2	5,1
16	4,1	5,1	6,3	7,7	4,5	4,1	5,1	6,3
20	4,8	5,9	7,3	9,0	5,3	4,8	5,9	7,3
25	5,6	6,9	8,5	10,5	6,2	5,6	6,9	8,5
30	6,4	7,9	9,7	12,0	7,0	6,4	7,9	9,7
50	9,2	11,3	13,9	17,1	10,1	9,2	11,3	13,8

Aggregate concrete units Group 3

f_b [N/mm ²]	General purpose mortar				Thin joint
	M2,5	M5	M10	M20	
2	0,9	1,0	1,0	1,0	0,8
4	1,4	1,7	2,0	2,0	1,3
6	1,8	2,3	2,8	3,0	1,8
8	2,3	2,8	3,4	3,9	2,1
10	2,6	3,2	4,0	4,9	2,5
12	3,0	3,7	4,5	5,6	2,8
16	3,7	4,5	5,6	6,8	3,5
20	4,3	5,3	6,5	8,0	4,1
25	5,0	6,2	7,6	9,4	4,8
30	5,7	7,0	8,6	10,6	5,4
50	8,1	10,0	12,3	15,2	7,7

The use of the above tables is allowed taking into account that:

- 1) CYS-EN 998-2 gives no limit for the thickness of joints made of thin layer mortar; the values in the above tables are based on a thickness of 0.5 - 3 mm to ensure that the thin layer mortar has the enhanced properties required to achieve the given values.
- 2) The thickness of the masonry is equal to the width or length of the unit, so that there is no mortar joint parallel to the face of the wall through all or any part of the length of the wall.
- 3) The coefficient of variation of the strength of the masonry units is not more than 25 %.
- 4) Where action effects are parallel to the direction of the bed joints, the characteristic compressive strength may also be determined from the tables, using the normalised compressive strength of the masonry unit, f_b , obtained from tests where the direction of application of the load to the test specimen is the same as the direction of the action effect in the masonry, but with the factor, δ , as given in EN 772, Annex A, not taken to be greater than 1,0. For Group 2 and 3 units, the value of f_k obtained from the tables should be multiplied by 0,5.
- 5) For masonry made of general purpose mortar where Group 2 and Group 3 aggregate concrete units are used with the vertical cavities filled completely with concrete, the value of f_b should be obtained by considering the units to be Group 1 with a compressive strength corresponding to the compressive strength of the units or of the concrete infill, whichever is the lesser.
- 6) When the perpendicular joints are unfilled, the tables may be used, with due consideration being given to any horizontal actions that might be applied to, or be transmitted by, the masonry.
- 7) For masonry made with general purpose mortar where there is a mortar joint parallel to the face of the wall through all, or any part, of the length of the wall, the values of f_k can be obtained by multiplying the values given in the tables by 0,8.

NA 2.6 Clause D.2 (1) Characteristic flexural strength

The characteristic flexural strength of masonry may be calculated using the clause 3.6.3(2) of CYS-EN 1996-1-1:2005+A1:2012, or from the tables bellow

Masonry unit	$f_{xk1,s}$ [N/mnm ²]			
	General purpose mortar		Thin layer mortar	Light weight mortar
	< M5	≥ M5		
Clay	0,10	0,10	0,15	0,10
Calcium silicate	0,05	0,10	0,20	not used
Aggregate concrete	0,05	0,10	0,20	not used
Autoclaved aerated concrete	0,05	0,10	0,15	0,10

Masonry unit		$f_{xk2,s}$ [N/mnm ²]			
		General purpose mortar		Thin layer mortar	Light weight mortar
		< M5	≥ M5		
Clay		0,20	0,40	0,15	0,10
Calcium silicate		0,20	0,40	0,30	not used
Aggregate concrete		0,20	0,40	0,30	not used
Autoclaved aerated concrete	$\rho < 400$ kg/m ³	0,20	0,20	0,20	0,15
	$\rho \geq 400$ kg/m ³	0,20	0,40	0,30	0,15

- (1) Provided that thin layer mortar and light weight mortars are M5, or stronger;
- (2) For masonry made with autoclaved aerated concrete units laid in thin layer mortar, f_{xk1} and f_{xk2} values may be taken from the above tables or from the following equations:

$$f_{xk1,s} = 0,035 f_b, \text{ with filled and unfilled perpend joints;}$$

$$f_{xk2,s} = 0,035 f_b, \text{ with filled perpend joints or } 0,025 f_b, \text{ with unfilled perpend joints.}$$

NA 2.7 Clause D.3 (1) Characteristic initial shear strength

The characteristic initial shear strength of masonry $f_{vko,s}$, provided that general purpose mortars made according to CYS-EN1996-2 do not contain admixtures or additives, may be taken from the table bellow.

Masonry unit	$f_{vko,s}$ [N/mmm ²]			
	General purpose mortar of Strength Class given		Thin layer mortar	Light weight mortar
Clay	M1 – M2	0,10	0,30	0,15
	M2,5 – M9	0,20		
	M10 –M20	0,30		
Calcium silicate	M1 – M2	0,10	0,40	0,15
	M2,5 – M9	0,15		
	M10 –M20	0,20		
Aggregate concrete Autoclaved aerated concrete	M1 – M2	0,10	0,30	0,15
	M2,5 – M9	0,15		
	M10 –M20	0,20		

NA 3 DECISION ON USE OF ANNEXES A AND C

NA 3.1 Annex A

Annex A may be used

NA 3.2 Annex C

Annex C may be used

NA 4 REFERENCES TO NON-CONTRADICTORY COMPLEMENTARY INFORMATION

None.

**NA to
CYS EN
1996-3:2006
(Including
AC:2009)**

CYPRUS ORGANISATION FOR STANDARDISATION

Limassol Avenue and Kosta Anaxagora 30,
2nd & 3rd Floor, 2014 Strovolos, Cyprus
P.O.BOX.16197, 2086 Nicosia, Cyprus
Tel: +357 22 411411 Fax: +357 22 411511
E-Mail: cystandards@cys.org.cy
Website: www.cys.org.cy
