

***NATIONAL ANNEX  
TO  
CYS EN 1996-1-2:2005  
(Including AC:2010)***

***Eurocode 6: Design of  
masonry structures***

***Part 1-2: General rules  
- Structural fire design***



**NATIONAL ANNEX**  
**TO**  
**CYS EN 1996-1-2:2005 including AC:2010 Eurocode 6:**  
**Design of masonry structures Part 1-2: General rules -**  
**Structural fire design**

This National Annex has been approved by the Board of Directors of the Cyprus Organisation for Standardisation (CYS) on 14.06.2019. Note:

*Correction on 23.08.2019 - NA 2.1 and NA 2.9 (Table 1)*

**Copyright**

*Right to reproduce and distribute belongs to the Cyprus Organisation for Standardisation*

*No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Cyprus Organisation for Standardisation.*

*If you have any questions about standards copyright, please contact Centre of Information and Customer Service at the Cyprus Organisation for*

*Standardisation phone: +357 22 411413/4 email: [c.service@cys.org.cy](mailto:c.service@cys.org.cy)*

## INTRODUCTION

This National Annex has been prepared by the CYS TC 18 National Standardisation Technical Committee of Cyprus Organisation for Standardisation. (CYS)

### NA 1 SCOPE

This National Annex is to be used together with CYS EN 1996-1-2:2005 including AC:2010.

Any reference in the rest of this text to CYS EN 1996-1-2:2005 means the above document.

This National Annex gives:

- (a) Nationally determined parameters for the following clauses of CYS EN 1996-1-2:2005 including AC:2010 where National choice is allowed (see Section NA 2)
  - 2.1.3(2)
  - 2.2(2)
  - 2.3(2)P
  - 3.3.3.1(1)
  - 3.3.3.2(1)
  - 3.3.3.3(1)
  - 4.5(3)
  - Annex B
  - Annex C
- (b) Decisions on the use of the Informative Annexes A, C, D, and E (see Section NA 3)
- (c) References to non-contradictory complementary information to assist the user to apply CYS EN 1996-1-2:2005+AC:2010. In this National Annex such information is not provided (see Section NA 4).

## NA 2 NATIONALLY DETERMINED PARAMETERS

### NA 2.1 Clause 2.1.3 Actions

(2) The values of maximum temperature rise during the decay phase are  $\Delta\Theta_1 = 200\text{K}$  and  $\Delta\Theta_2 = 240\text{K}$ .

### NA 2.2 Clause 2.2 Actions

(2) The emissivity value,  $\epsilon_m$ , of a masonry surface depends on the material of the masonry and is given in CYS EN 1991-1-2.

### NA 2.3 Clause 2.3 Design values of material properties

(2)P The recommended value of  $\gamma_{M,\text{fl}} = 1.0$  for both mechanical and thermal properties of masonry is adopted.

### NA 2.4 Clause 3.3.3.1 Thermal elongation

(1) The thermal elongation of masonry should be determined from tests or from a database. The variation of thermal elongation with temperature for some materials is given in Annex D.

**NA 2.5 Clause 3.3.3.2 Specific heat capacity**

(1) The specific heat capacity of masonry,  $c_a$ , should be determined from tests or from a database. The variation of specific heat capacity with temperature for some materials is given in Annex D.

**NA 2.6 Clause 3.3.3.3 Thermal conductivity**

(1) The thermal conductivity,  $\lambda_a$ , of masonry should be determined from tests or from a database. The variation of thermal conductivity with temperature for some materials is given in Annex D.

**NA 2.7 Clause 4.5 Assessment by tabulated data**

(3) The safety factor value for use in fire tests,  $\gamma_{G10}$  are taken to be between 3 and 5.

**NA 2.8 Clause Annex B- Tabulated fire resistance of masonry**

The recommended values of  $t_F$ ,  $I_F$  given in Tables N.B.1 to N.B.5 are adopted.

**NA 2.9 Clause Annex C- Simplified calculation model**

The recommended values of constant  $c$  are given in Table 1 (CYS) below.

**Table 1 (CYS). Values of constant,  $c$ , and temperature  $\theta_1$  and  $\theta_2$  by masonry material**

Masonry units and mortar (surface unprotected) according to 1.1 (2)	Values of constant $c$	Temperature °C	
		$\theta_2$	$\theta_1$
Clay units with general purpose mortar	$c_{cl}$	600	100
Calcium silicate units with thin layer mortar	$c_{cs}$	500	100
Lightweight aggregate units (pumice) with general purpose mortar	$c_{la}$	400	100
Dense aggregate units with general purpose mortar	$c_{da}$	500	100
Autoclaved aerated units with thin layer mortar	$c_{aac}$	<b>400</b>	200

**NA 3 DECISION ON USE OF THE INFORMATIVE ANNEXES**

**NA 3.1 Annex A**

Annex A may be used

**NA 3.2 Annex C**

Annex C may be used

**NA 3.3 Annex D**

Annex D may be used

**NA 3.4 Annex E**

Annex E may be used

**NA 4 REFERENCES TO NON-CONTRADICTIONARY COMPLEMENTARY INFORMATION**

None



**NA to  
CYS EN  
1996-1-2:2005  
(Including  
AC:2010)**

**CYPRUS ORGANISATION FOR STANDARDISATION**

Limassol Avenue and Kosta Anaxagora 30,  
2<sup>nd</sup> & 3<sup>rd</sup> Floor, 2014 Strovolos, Cyprus  
P.O.BOX.16197, 2086 Nicosia, Cyprus  
Tel: +357 22 411411 Fax: +357 22 411511

E-Mail: [cystandards@cys.org.cy](mailto:cystandards@cys.org.cy)

Website: [www.cys.org.cy](http://www.cys.org.cy)